

502 Karna-Flex

DESCRIPTION:

Karnak Karna-Flex is an elastomeric, thermoplastic-rubber sealant formulated for use on properly prepared metal, concrete, spray polyurethane foam and plywood roof substrates. Its ease of application, superior adhesion, elasticity and durability make Karna-Flex an ideal repair sealant. Available in a brush mastic or caulking cartridge.

USES:

Karna-Flex's elastomeric properties make it an excellent sealant for prepared metal, concrete, spray polyurethane foam and plywood roof system details. Ideal for sealing and waterproofing metal roof seams and splits, gutters, fasteners, pinholes in metal, flashing and curb details. Also use to seal around skylights, penetrations and roof top equipment.

FEATURES, BENEFITS AND ADVANTAGES:

1. One component—no need to intermix with other materials.
2. Easy application by brush or caulking gun.
3. Superior film—forms a durable, weather resistant elastomeric membrane.
4. Has superior adhesive and cohesive strength.
5. Low temperature flexibility—specially selected polymers and resins impart superior low temperature properties to the coating.

SURFACE PREPARATION:

All surfaces to be sealed must be clean, dry and free from oil, grease and other foreign matter.

APPLICATION:

Apply Karna-Flex by brush or caulking gun in the following manner

1. Horizontal Seams and Cracks 1/16" wide or larger.
 - Using Karnak 550 Patch-N-Go Fleece Self Sealing Tape, adhere tape to crack as directed per production application guidelines. Apply Karna-Flex at an average thickness of 1/16" to completely cover the polyester face of the tape and feather out.

KARNAK

330 CENTRAL AVENUE, CLARK, NJ 07066
732-388-0300 • 800-526-4236 • FAX: 732-388-9422
WEB: <http://www.karnakcorp.com>

502 Karna-Flex

- Or, using Karnak Resat-Mat, apply Karna-Flex at an average thickness of 1/16" to completely cover the crack. Immediately embed one layer of Resat-Mat and cover with another application of Karna-Flex. Make sure to smooth the fabric out completely and cover.

Product will cure within approximately 24 hours. If continuing with 502 Elasto-Kote System is desired, allow all repairs to cure before proceeding.

PHYSICAL PROPERTIES:

Weight per Gallon:	9.5 lbs
Color:	White, Black, (Gray available upon request, full skid only)
Tensile Strength:	40 psi
Elongation:	500%
Low Temp Flex	-40°F
ASTM-C-734:	No cracking/pass
Recovery:	75% min.
VOC:	Please visit www.karnakcorp.com for latest VOC content as products are updated to comply with the most current VOC regulations

NOTE:

Karna-Flex is not recommended for use over asphaltic substrates. Contact Karnak Corporation for alternative systems.

KARNAK

330 CENTRAL AVENUE, CLARK, NJ 07066
 732-388-0300 • 800-526-4236 • FAX: 732-388-9422
 WEB: <http://www.karnakcorp.com>

502 Karna-Flex

CAUTION:

Do not use near open flame. Avoid breathing solvent fumes and prolonged contact with skin. Do not take internally. If swallowed, do not induce vomiting. Call a physician immediately. KEEP OUT OF REACH OF CHILDREN. Keep container covered when not in use. Do not thin. Dispose of in an environmentally safe manner. Cover air intakes during application and while drying.

COLD-PROCESS SYSTEMS AND COATINGS, EITHER EMULSION OR SOLVENT BASED, SHOULD ONLY BE INSTALLED ON DECKS WITH POSITIVE DRAINAGE.

PER NRCA, (NATIONAL ROOFING CONTRACTORS ASSOCIATION) "THE CRITERIA FOR JUDGING PROPER SLOPE FOR DRAINAGE IS THAT THERE BE NO EVIDENCE OF STANDING WATER ON THE DECK 48 HOURS AFTER IT STOPS RAINING."

PACKAGING:

Karna-Flex:	3 Gallon Buckets
	30 oz. Caulking Cartridges

If further information is needed, contact Karnak Technical Services at 1-800-526-4236.

Please see page 222 for additional mold and safety information.

KARNAK

330 CENTRAL AVENUE, CLARK, NJ 07066
732-388-0300 • 800-526-4236 • FAX: 732-388-9422
WEB: <http://www.karnakcorp.com>